

# APPLYLABWORK PRINTING INSTRUCTIONS

## FORM 2 & 3 PRINTER Laser ROBUST Champagne (PT-RO001CP)

### Check:

- UV optical pathways are clean
- Vat is free of defect
- Resin is well shakened

### Open-Mode (Form2):

Printer at idle

1. Tap touchscreen “printer” icon, open “Settings” menu
2. Select Open Mode
3. Select On

### Print in Cartridge Mode (Form2 & 3):

Refill corresponding cartridge e.g. FormLabs Grey version 4 cartridge. Open air vent, turn cartridge upside down, drip dry through air vent for 10 mins to avoid cross contamination, refill, shake well for 2 mins, insert & print (may work up to 2 refills before locked by FL software).

**Warning: Cross contamination of resins could cause size inaccuracy or wavy line. LT vat recommended.**

Alternative Solution: [North America](#) , [Other Regions](#)

### PreForm Setting:

Select Printer: Form2 or Form3

Material Select: **Grey and V4**

Suggest Layer Thickness 100~25

**JOB SETUP**

Printer

VIRTUAL PRINTER  
Form 3

Material

Resin: Grey

Version: V4 (FLGPGR04)

Print Setting: Default

Layer Thickness (microns)

Fastest Print | 160 | 100 | 50 | 25 | Highest Resolution

Cancel Apply

### Washing:

IPA 95%, maximum for up to 5 minutes, gently shake-off / blow-off excess IPA quickly, set print in a shaded airy place to dry completely before curing.

Extended time in IPA causes deformation. Dried print might be a little tacky to touch.

### Post-curing (Necessary):

For optimal material performance: FormCure 60 °C / 30~60 mins, pending on wall thickness and model size. Start FormCure from room temperature.

### Storage:

- Keep resin away from heat & light.
- NOT accessible to children.
- Filter used resins before storage.

### Note:

- Keep print environment well ventilated.
- Avoid direct contact to skin or eyes. Rinse cautiously with water / soap and water for several minutes if contact to eyes / skin.
- Wear chemically-resistant gloves like nitrile or neoprene (not latex) when handling.
- DO NOT pour uncured resin down the drain. Abandoned resin can be cured by sunlight before discarding.
- Unless specifically indicated, ROBUST resin is NOT approved for use with food, drink, or on/in the human body.

### WARNING:

Contact may cause eye or skin irritation and allergic reaction.