

CARIMA NON-TOXIC RESIN SETTINGS FOR PHROZEN SONIC MINI 8K

- **Bottom exposure:** 40s
- **Bottom layers:** 3-6 layers
- **50 micron exposure:** 3s
- **100 micron exposure:** 3.6s

POST-PROCESSING

- **Postcure:** 1-3 minutes