

PEEK


High Performance



| THERMAL DATA | CONDITIONS | TEST METHOD | TYPICAL VALUE |
|----------------------|-----------------|-------------|--|
| Melting Point | | ISO 11357 | 343 °C |
| Glass Transition | Onset | ISO 11357 | 143 °C |
| Thermal Conductivity | Along flow, 23° | ISO 22007-4 | 0.32 W m ⁻¹ K ⁻¹ |

| Mechanical Properties* | CONDITIONS | TEST METHOD | TYPICAL VALUE |
|------------------------|----------------------|-------------|------------------------|
| Tensile Strength | Yield, 23 °C | ISO 527 | 105 MPa |
| Tensile Elongation | Break, 23 °C | ISO 527 | 30% |
| Tensile Modulus | 23 °C | ISO 527 | 4.1 GPa |
| Flexural Strength | At 3,5% strain, 23 ° | ISO 178 | 130 MPa |
| Flexural Modulus | 23 °C | ISO 178 | 3.9 GPa |
| Charpy Impact Strength | Notched, 23 °C | ISO 179/1eA | 4.2 kJ m ⁻² |
| Izod Impact Strength | Notched, 23 °C | ISO 180/A | 5.0 kJ m ⁻² |

*Mechanical properties refer to the amorphous phase of the material



General information

PEEK is a high-performance polymer of a PAEK family that offers a unique combination of properties. 3D printed PEEK models combine resistance to various chemicals, wear, and fatigue resistance, exceptionally high-temperature resistance as well as very good mechanical properties. PEEK mechanical properties are one of the highest of all known thermoplastic materials. PEKK and PEEK are extremely resistant to external conditions.

PEEK is flame resistant (Class V-0 according to UL 94) with low smoke and toxicity. It provides high resistance for a wide range of chemicals, also in increased service temperatures.

PEEK can also be used as an effective electric insulator in a wide range of frequencies with outstanding thermal and environmental resistance.

Usually, the desirable state of PEEK is the semi-crystalline, which can be achieved after the annealing process of the printed model. In order to reach high dimensional accuracy of the models and the quality of the expected prints, PEEK needs high extrusion temperature, heated bed, and the actively heated print chamber.

Detailed data are available on our website
www.3dgence.com

AMERICAS

3DGence America Inc.
 Dallas, Texas,
 USA

+1.855.466.3813
inquiries@3dgence.com

EUROPE

3DGence GmbH,
 Gradignanstraße 4
 64319 Pfungstadt, Germany

+49 6157 9118972
cs@3dgence.com

3DGence sp. z o.o.
 Graniczna 66
 44-178 Przyszowice, Poland

+48 32 438 98 63
cs@3dgence.com