

ESM-30

Soluble Support Material



General properties

Material	Proprietary acrylic copolymer
Colour	Natural
Transparency	Transparent
Net weight filament	0,75 kg
Spool dimension (Ø x height)	200x55 mm
Diameter	1,75 mm
Density (21.5°C)	1,1 g/cm ³
Melt flow index at 200°C, 10kg	7 MFR
Glass transition temperature	130°C

Detailed data are available on our website
www.3dgence.com

AMERICAS

3DGence America Inc.
 Dallas, Texas,
 USA

+1.855.466.3813
inquiries@3dgence.com

EUROPE

3DGence GmbH,
 Gradignanstraße 4
 64319 Pfungstadt, Germany

+49 6157 9118972
cs@3dgence.com

3DGence sp. z o.o.
 Graniczna 66
 44-178 Przyszowice, Poland

+48 32 438 98 63
cs@3dgence.com